



Element Materials Technology
662 Cromwell Avenue
St Paul, MN
55114-1720 USA

P 651 645 3601
F 651 659 7348
T 888 786 7555
info.stpaul@element.com
element.com

Company: Haala Industries
Address: 2101 Hwy. 4 South
Sleepy Eye, Minnesota 56085
Attn: Mr. Steve Haala

Report Number: ESP010867P.2
Date: August 21, 2012
Page: 1 of 6

Tension Testing of Lifting Insert/Anchor

I hereby certify that this plan, specification or report was prepared by me or under my direct supervision and that I am a duly Registered Engineer under the laws of the State of Minnesota.

Jason R. Steen, P.E.
Registration No. 43491

Prepared By:

Jason R. Steen, P.E.
Staff Engineer, Building Products Evaluation
Phone: 651-659-7259

Reviewed By:

John D. Lee, P.E., LEED AP
Manager, Building Products Evaluation
Phone: 651-659-7408

It is our policy to retain components and sample remnants for 30 days from the report date, after which time they may be discarded. The data herein represents only the item(s) tested. This report shall not be reproduced, except in full, without prior permission of Element Materials Technology.

This document contains technical data whose export and re-export/retransfer is subject to control by the U.S. Department of Commerce under the Export Administration Act and the Export Administration Regulations. The Department of Commerce's prior written approval is required for the export or re-export/retransfer of such technical data to any foreign person, foreign entity or foreign organization whether in the United States or abroad.

These commodities, Technology, or software were exported from the United States in accordance with the Export Administration Regulations. Diversion contrary to U.S. law is prohibited.

This project shall be governed exclusively by the General Terms and Conditions of Sale and Performance of Testing Services by Element Materials Technology. In no event shall Element Materials Technology be liable for any consequential, special or indirect loss or any damages above the cost of the work.

INTRODUCTION:

This report presents the results of testing performed by Element Materials Technology; on Haala Industries precast concrete insert/anchor. The scope of our work was limited to the following:

1. Conduct pull out testing of the insert/anchor.
2. Prepare a report in regards to the results.

Our work was authorized by Mr. Steve Haala of Haala, Industries on July 24, 2012, and approved verbally.

CONCLUSION:

The precast concrete insert/anchor was tested on August 1, 2012. One sample was loaded to failure in accordance with the Test Procedures found below. The failure mode for sample consisted of concrete split. **The ultimate load of the sample was 21,484 pounds.**

TEST SAMPLE:

The insert/anchor samples were submitted by the client to Element Materials Technology, St. Paul, Minnesota, where they were received on July 17, 2012. A single concrete block with one embedded lifting insert/anchor was submitted. Haala Industries Insert/Anchors are used with precast concrete. The top of the insert/anchor was installed below the surface of the concrete approximately 2" in an access pocket. Sample drawing as received is shown below.

TEST PROCEDURES:

The tests were conducted as tension tests in accordance with the test provisions listed in ASTM E 488 - 96 "standard Test Method for Strength of Anchors in Concrete and Masonry Element". The International Accreditation Service, Inc. (IAS) issued a Certificate of Accreditation TL-217, January 12, 2012, listing Element Materials Technology as an accredited laboratory for a scope of services that includes testing to ASTM E 488.

CONCRETE:

The concrete structural member was designed and cast by others. No description of the mix design was received for this concrete. No concrete strength was determined at time of testing.


ANCHOR INSTALLATION:

The concrete insert/anchor tested in this project was pre-installed by the client. Element has no information as to the installation of the anchor in general.

EQUIPMENT:

The test load was measured with load cells, CME-SPC-406 calibration due on 05/11/13.

TEST RESULTS:

 Element Materials Technology - St. Paul Project No. ESP010867P		Sample Information Cast In Place Loop Anchor and Strand Anchors			Tests Performed 90-Degree Tension																																																																																																																																			
Setup and Installation Technicians: S. Palodichuk, N. Holderbaum Concrete Cast By: Contractor Anchors Installed By: Contractor		Test Equipment System Number: CME-SPC-910 Load Cell: CME-SPC-406 Caliper: CME-SPC-300			Calibration Due Date 5/26/2013 5/11/2013 5/22/2013																																																																																																																																			
Test #2 Information Anchor System: Part # 3836 Cable Anchor Material: Steel Strands Anchor Location: Side of Block - Form Finish Anchor Size Before(in.): 0.375" Diameter Anchor Size After(in.): 0.275" Diameter Block Number: 48 2B 2X3C Cast Date: 5/21/2012 Install Depth (in.): Unknown Confined Test: No																																																																																																																																								
<table border="1"> <thead> <tr> <th>Test Number</th> <th>2</th> <th></th> <th></th> <th></th> <th></th> <th></th> <th></th> <th></th> <th></th> </tr> </thead> <tbody> <tr> <td>Test Data</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Test Date</td> <td>08/01/12</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Test Time</td> <td>10:20 AM</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Install Date</td> <td>05/21/12</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Ultimate Load (lbf)</td> <td>21484</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Failure Mode</td> <td>CS</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Test Duration (sec)</td> <td>83</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Test Fixture Type</td> <td>Clevis</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Test Fixture Diameter</td> <td>1.060</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Outside Anchor Span</td> <td>2 1/4</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Anchor Height Before</td> <td>n/a</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Anchor Height After</td> <td>n/a</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> </tbody> </table>		Test Number	2									Test Data										Test Date	08/01/12									Test Time	10:20 AM									Install Date	05/21/12									Ultimate Load (lbf)	21484									Failure Mode	CS									Test Duration (sec)	83									Test Fixture Type	Clevis									Test Fixture Diameter	1.060									Outside Anchor Span	2 1/4									Anchor Height Before	n/a									Anchor Height After	n/a													
Test Number	2																																																																																																																																							
Test Data																																																																																																																																								
Test Date	08/01/12																																																																																																																																							
Test Time	10:20 AM																																																																																																																																							
Install Date	05/21/12																																																																																																																																							
Ultimate Load (lbf)	21484																																																																																																																																							
Failure Mode	CS																																																																																																																																							
Test Duration (sec)	83																																																																																																																																							
Test Fixture Type	Clevis																																																																																																																																							
Test Fixture Diameter	1.060																																																																																																																																							
Outside Anchor Span	2 1/4																																																																																																																																							
Anchor Height Before	n/a																																																																																																																																							
Anchor Height After	n/a																																																																																																																																							
Failure Mode Index PO - Anchor Pull Out PT - Anchor Pull Through		CC - Concrete Cone CE - Concrete Edge CP - Concrete Pryout CS - Concrete Split			SB - Steel, Body ST - Steel, Threads SN - Steel, Neck TN - Mating Element																																																																																																																																			
		BB - Borehole Bond BE - Bond Element BA - Bond Anchor TI - Internal Thread																																																																																																																																						

REMARKS:

The remains of the concrete sample and insert/anchor test specimens are subject to disposal thirty days from the date of this report.

PHOTOGRAPHS:



Figure 1 – 90-degree Tension Test Set-up




Figure 2 – Tension Failure Mode

PRODUCT DRAWING:

3/8" cable, 7 wire EHS class A galvanized

Dimensions are Inches

Overall length 36"



1201 Hwy. 4 South
P.O. Box 389
Sleepy Eye, MN 56085

STEVE HAALA OFFICE: 507-794-5821

Cell: 507-920-9180
Home: 507-794-4848

Fax: 507-794-5823
Website: www.haala.com
Email: steve@haala.com

DATE : 03/28/08
DRAWN BY: CALEB

STEEL PROPERTIES:

NATIONAL STRAND
A HEICO WIRE GROUP COMPANY

P.O. Box 96149
 12611 Cain Circle (77015)
 Houston, Texas 77213-6149
 Phone: (713) 455-2888
 Fax: (713) 455-3888

CERTIFICATE OF COMPLIANCE

CUSTOMER: HAALA INDUSTRIES, INC		DATE: 1/31/2012	
CUSTOMER PO #: 33060		SALES ORDER #: 116280	
PRODUCT	DIAMETER	PACKAGE	SPECIFICATION
GALVANIZED STEEL STRAND EXTRA HIGH STRENGTH 7-WIRE CLASS "A"	3/8"	30 X 5000' REELS	ASTM-A475

TEST RESULTS						
HEAT #	SIZE	MINIMUM BREAKING STRENGTH (LBS)	ELONGATION PER 24"	WEIGHT OF COATING (OZ. PER FT ²)	MANDREL ADHERENCE & DUCTILITY	LAY LENGTH
N/A	3/8"	15400	4% min.	0.85	PASS	5.40"

National Strand certifies that the above test results are representative of those contained in company records and were obtained using methods consistent with the requirements of applicable specifications.

The above products were manufactured in the USA.



Juan Garza
 Quality Department